



Polymers



Chemical &  
Aromatics



Fuel & Feeds  
Stock

# LDPE LF0200

FILM GRADE

Property	Test Method	Value	Unit
MFI (190°C/2.16KG)	ASTM D-1238	1.7-2.3	gr/10 min
DENSITY	TSTM 209 B	0.918-0.922	gr/ml
SOFTENING POINT	ASTM D-1525	92-96	°C
HAZE	ASTM D-1003	15 MAX	%
GLOSS @ 60°C	ASTM D-523	60 min	gu
Elongation @Break (MD)	ASTM D-882	330 min	%
Elongation @Break (TD)	ASTM D-882	600 min	%
tensile @Break (MD)	ASTM D-882	160 min	kg/cm2
dart impact	ASTM D-1709	100 min	gr

## APPLICATION

film & small bag

TSTM= TOYO SODA STANDARD TESTMETHOD