

TECHNICAL DATA SHEET

Product Data sheet: BG-LL 22B03

Linear low Density PE	Film	
LLDPE: BG-LL 22B03	Density: 0.920 - 0.924	MFI: 2.8 - 3.2
Feature: <ul style="list-style-type: none"> Comonomer:butane-1(c4) High stiffness 	Application: <ul style="list-style-type: none"> High stiffness blown & cast film Blending Lamination 	Additives: <ul style="list-style-type: none"> Acid scavenger Antioxidants Lubricant

Material properties (this data are typical values and shall not be construed as product specifications.)

Resin properties	unit	condition	Typical value	Test method
Melt index	g/10 min	190°C/2.16 kg	2.8-3.2	ASTM D1238
Density	g/l	23°C	0.920-0.924	ASTM D1505
F/E Ratio	-	-	<30	ASTM D1238
Yellowness Index	-	-	0.5	ASTM D1925
Ti content	ppm wt	-	2	MTM 15636
Fish Eyes	Gels/m ²	-	60-100	MTM 17108
Haze	%	-	2	ASTM D1003
Gloss 45°	%O	-	90	ASTM D2457
Dart impact	gr	-	70	ASTM D1709
Tensile modulus	2% sec	MD	115	ASTM D882
	Mpa	TD	120	ASTM D882
Tensile strength	Ultimate	MD	50	ASTM D882
	Mpa	TD	24	ASTM D882
Elongation	@Break	MD	480	ASTM D882
	%	TD	850	ASTM D882
Elmendorf tear	g	MD	90	ASTM D1922
		TD	350	ASTM D1922